



CLEAR SHOT™

ENGINEERING DATA SHEET

- **Weight per gallon:** 8.6 – 8.8 lbs
- **Flash Point:** 110°F (Flash Point is the minimum temperature at which an open flame can ignite the product.)
- **Volatile Organic Content (VOC):** 339 g./liter
- **Viscosity:** 160 cP
- **Theoretical coverage:** 350-450 sq. ft. per gal. Depending on surface.
- **Solids by volume:** 80 ± 2%
- **Recommended dry film thickness:** 2-4 mils DFT (applied in 1-2 wet coats)
- **Temperature Resistance:** Continuous: 314°F
- **Chemical Resistance:** Excellent
- **Recoatibility:** With Clear Shot after 4-48 hours.
- **Color/Finish:** Clear Gloss
- **Cure Time:** Handle: 2-4 Hours; Touch: 2-4 hours. Depending on ambient temperature and relative humidity. Recoat: 4-48 hours. Cure time varies with relative humidity, temperature and thickness of film (48-72 hours).
- **Shelf Life:** 2 years, after ship date, unopened, stored between 50°-100°F.
- **Application Temperature:** 32°F-110°F (0°C-43°C)
- **Compatibility:** Compatible with all coatings that are compatible with MCUs (Moisture-cured Urethane); always refer to the coating manufacturers guidelines for application and compatibility.

Typical Uses

Clear Shot can help rejuvenate and restore faded or oxidized surfaces to like new condition. Protectant for mostly all surfaces from harsh elements.

Product Description

Clear Shot is one of the strongest and clearest single component protective coatings available. Rust Bullet Clear Shot is a single component urethane that won't crack, chip, yellow, or peel and dries to an incredibly hard, water clear finish. For the ultimate protection, apply Clear Shot as a topcoat over our patented Rust Bullet Standard or Rust Bullet Automotive Formulas. Clear Shot is UV resistant, scratch and chip resistant. Clear Shot can be brushed, rolled or sprayed.

Advantages of Clear Shot

- Non-yellowing
- Easy to apply on rusted or clean surfaces
- Excellent resistance to weather and mechanical abuse
- Excellent chemical resistance
- Excellent abrasion resistance
- Excellent adhesion
- UV resistant
- Self leveling
- Flexible
- Strong

Safety Information

Avoid ingestion, contact with skin or eyes. The use of safety glasses and chemical gloves is recommended. When brushing, rolling or spraying, appropriate NIOSH approved respiratory protection is recommended. See [Safety Data Sheet](#) for complete safety data before use, available at www.RustBullet.com. It is the applicator's responsibility to understand these safety precautions and the work environment, to protect themselves and/or others.

Surface Preparation

Surface must be free of contaminates, such as, loose rust, oil, grease, wax, moisture, salts etc. This may be achieved by light scraping; a detergent or solvent wipe may be used if necessary. For more information:

RUST BULLET LLC ~ 300 Brinkby Avenue, Suite 200, Reno, NV 89509 USA (800) 245-1600, (775) 829-5606 www.rustbullet.com

Information contained herein is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee. Since the conditions of use are beyond our control, Rust Bullet, LLC (the Company), disclaims any liability incurred in connection with the use of our products and information contained herein. No person is authorized or empowered to make any statement or recommendation not contained herein, any such statement or recommendation so made shall not bind the Company. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use. The information is furnished upon the condition that the recipient shall make his own determination concerning suitability for his particular application.